

S/N 09/847,479
Docket: FIS920000077US1

IN THE CLAIMS:

Please revise the claims to read as follows:

1. (Currently Amended) A method of fabricating an electronic chip on a wafer, comprising:

developing on a surface of said wafer a first mask at a predetermined lower resolution; and

etching said first mask under a first set of conditions for a predetermined period to achieve a higher resolution mask, said higher resolution achieving a critical dimension of that is below 100 nm or less, said first set of conditions including a tuning parameter to independently control a line width variation tolerance of isolated features relative to nested features.

2. (Previously Amended) The method of claim 1, wherein said first mask comprises an organic photo-sensitive resist material.

3. (Original Claim) The method of claim 1, wherein said first set of conditions comprises an oxygen and nitrogen plasma etch, wherein

a flow ratio of oxygen to nitrogen is between 0.25 and 2.5;

a setting of an RF power is in the range of 50 to 200 watts; and

a setting of a pressure is between 10 and 45 mTorr.

4. (Original Claim) The method of claim 1, further comprising:

S/N 09/847,479
Docket: FIS920000077US1

etching, under a second set of conditions for a second predetermined period, at least one layer of said wafer or at least one layer of material deposited on said wafer, to remove at least a portion of said at least one layer to produce features at said higher resolution.

5. (Original Claim) The method of claim 4, wherein said second set of conditions comprises a CF₄/ CHF₃/ Argon based hard-mask process for etching a gate oxide layer.

6. (Original Claim) The method of claim 5, wherein said second set of conditions further comprises a range of 20-80 sccm (standard Cubic Centimeters/Minute) for CF₄, 5-15 sccm for CHF₃, and 40-200 sccm for argon.

7. (Currently Amended) A method of fabricating at least one electronic device or circuit on a wafer, comprising:

cont.
B1
developing a first mask on an outer surface of said wafer or of a layer of material deposited on said surface to define a pattern for at least part of a structure or circuit component for said electronic device or circuit, said first mask comprising an organic photo-sensitive resist material;

performing a trimming process on said first mask to adjust dimensions of said pattern, said trimming process achieving a critical dimension of that is less than 100 nm or less; and using said trimmed first mask as a hard mask for an etching process to remove material from at least one layer below said hard mask, wherein

said trimming process includes a tuning parameter to independently control a line width variation tolerance of isolated features relative to nested features.

S/N 09/847,479
Docket: FIS920000077US1

8. (Original Claim) The method of claim 7, wherein said trimming process of said first mask comprises an oxygen and nitrogen plasma etch, wherein

- a flow ratio of oxygen to nitrogen is between 0.25 and 2.5;
- a setting of an RF power is in the range of 50 to 200 watts; and
- a setting of a pressure is between 10 and 45 mTorr.

9. (Original Claim) The method of claim 7, wherein said etching process to remove material from said at least one layer below said hard mask comprises a CF₄/ CHF₃/ Argon based hard-mask process for etching a gate oxide layer.

10. (Original Claim) The method of claim 9, wherein conditions of said etching to remove material off at least one layer below said hard mask comprises a range of 20-80 sccm (standard Cubic Centimeters/Minute) for CF₄, 5-15 sccm for CHF₃, and 40-200 sccm for argon.

*P1
CONT.*

11. (Currently Amended) A method of controlling line width variation tolerances during fabrication of electronic devices or circuits on a wafer, comprising:

- developing a first mask on an outer surface of said wafer or of a layer of material deposited on said surface to define a pattern for at least part of a structure or circuit component for said electronic device or circuit, said first mask comprising an organic photo-sensitive resist material;

S/N 09/847,479
Docket: FIS920000077US1

performing a trimming process on said first mask to adjust dimensions of features of said first mask, said trimming process achieving a critical dimension of that is less than 100 nm or less; and

using said trimmed first mask as a hard mask for an etching process to remove material from at least one layer below said hard mask, wherein

said trimming process of said first mask comprises an oxygen and nitrogen plasma etch, in which:

a flow ratio of oxygen to nitrogen is between 0.25 and 2.5;

a setting of an RF power is in the range of 50 to 200 watts; and

a setting of a pressure is between 10 and 45 mTorr.

12. (Currently Amended) A method, during fabrication of electronic devices or circuits on a wafer, said devices or circuits having both isolated features and nested features, of controlling line width variation tolerances of said isolated features relative to said nested features while independently achieving a target critical dimension that is less than 100 nm, comprising:

establishing a first set of conditions for an RF etch process that achieves said target critical dimension, said critical dimension being 100 nm or less; and

controlling a level of said RF power as a parameter to independently control said line width variation tolerance of said isolated features relative to said nested features.

13. (Original Claim) An electronic device or circuit fabricated at least in part by the method defined in claim 1.

S/N 09/847,479
Docket: FIS920000077US1

14. (Original Claim) An electronic device or circuit fabricated at least in part by the method defined in claim 7.

15. (Original Claim) An electronic device or circuit fabricated at least in part by the method defined in claim 11.

16. (Original Claim) An electronic device or circuit fabricated at least in part by the method defined in claim 12.

17. (Currently Amended) An electronic apparatus comprising:

at least one circuit chip having a critical dimension of that is less than 100 nm or less, said critical dimension having been achieved by a fabrication process of said circuit chip, said circuit chip fabrication comprising:

forming a soft mask as a mask for a hard mask, said soft mask using a lithographic process having a first resolution; and

trimming said soft mask to achieve a second resolution higher than said first resolution, said trimming using an etching process having an adequate Across Chip Linewidth Variation (ACLV) tunable parameter to achieve said critical dimension of 100 nm or less.

18. (Currently Amended) The electronic apparatus of claim 17, wherein said ACLV tunable parameter is set by establishing a power level of an RF etch process for said soft mask trimming.

S/N 09/847,479
Docket: FIS920000077US1

19. (Previously Added) The electronic apparatus of claim 18, wherein said RF etch process comprises an oxygen and nitrogen plasma etch.

20. (Previously Added) The electronic apparatus of claim 19, wherein said oxygen and nitrogen plasma etch comprises:

BD
Cont.
a flow ratio of oxygen to nitrogen is between 0.25 and 2.5;

a setting of an RF power is in the range of 50 to 200 watts; and

a setting of a pressure is between 10 and 45 mTorr.